

Ceramic laminate veneers- An innovative approach in esthetic dentistry

Jaydeepsinh Dabhi^{1,*}, Poorvin G.Prajapati², Arpit Viradiya³, Shashank Kumar Mishra⁴, Bhagyashree Bhatt⁵

¹PG Student, Darshan Dental College & Hospital, Udaipur, Rajasthan, ^{2,3}Private Practitioner, Ahmedabad, Gujarat, ³Surat, Gujarat, ⁴Senior Lecturer, Chhattisgarh Dental College & Research institute, Rajnangaon, Chhattisgarh, ⁵Intern, Pacific Dental College & Hospital, Udaipur, Rajasthan, India

***Corresponding Author:**

Email: jaydeep311@gmail.com

Abstract

The purpose of this article is to describe the possibility of enhancing dental aesthetics with low-thickness glass ceramics without most important tooth instruction for patient with small to moderate anterior dental fluorosis and discoloration. Proper treatment planning is being considered as the important phase as it considers the preservation of the enamel and dentine as well. Moreover, the anterior guidance can also be altered with the improvement in the esthetic consideration. It can be concluded that the low thickness glass ceramic laminate veneers provides excellent esthetic outcome while maintaining the tooth anatomy.

Keywords: Laminates, Dental Veneers, Ceramic veneers, Dental ceramics, Dental esthetics.

Introduction

The esthetic dentistry, regarding the anterior teeth has a greater difficulty in the practice. As the evaluation in the dental materials is occurring, the better restorative materials like composite resins, Porcelain Fused Metal crowns, all ceramic crowns, ceramic veneers and zirconia crowns became available for treatment. This environment create the best of the treatment option for the excellent esthetic outcome.

Ceramic veneers can be considered as the one of the best treatment option in improving the esthetics. They are indicated in the condition where mild to moderate fluorosis is present and anterior dental wear. The important properties of the ceramics' include biocompatibility, colour stability, opaqueness and esthetic outcome.¹ For the successful permanent restoration, the minimal invasive treatment approach is being considered as the most important phase.^{2,3} Thus, the use of the laminate veneers have been markedly improved.

Treatment planning is the essential part of the esthetic dentistry. The success of the ceramic veneers depends upon the remaining amount of the enamel and dentinal structures and the preparation design.⁴ The smile designing and the cosmetic interferences have greater results due to treatment planning. Thus, the good interaction between the dentist and the well trained lab technician helps in achieving the better results. The thorough knowledge of the various ceramic types and the step by step cementation procedure have a huge impact on the good esthetic prognosis.⁵ Therefore, the purpose of this article is to minimally prepare the tooth and achieving the beautiful smile.

Case Report

A 32 year old male patient reported to the department of conservative dentistry and Endodontics, Pacific dental college and Hospital, Udaipur with the

chief complaint of various white spots on the front surface of the upper teeth since 10 years. On clinical examination, after evaluating the shape, opaqueness, and size of the white spots, it was diagnosed as generalised moderate fluorosis in relation to maxillary anterior teeth on both the side. (Fig. 1).



Fig. 1: Pre operative Photograph

Due to case characteristics and the esthetic need of the patient, the treatment plan was decided for least invasive and long lasting Ceramic laminate veneers for six anterior teeth. Diagnostic casts were made and were used for treatment designing.

The tooth preparation was started with a #2135-diamond bur (KG Sorensen, Barueri, SP, Brazil) for each tooth. A careful labial reduction was carried out to provide minimum of 0.3 to 0.6 mm. The entire preparation were done on the enamel surfaces with no dentine exposure. (Fig. 2)



Fig.2: Completed Preparation Restricted to Enamel

The shade selection were done prior to the preparation in natural light source. The gingival cord was placed using gingival liquid containing adrenaline (Ultrapak Cord #000, Ultradent Products Inc., South Jordan, UT, USA) to provide transient gingival enlargement(Figure-3).The impressions were taken with heavy bodied impression material on trays and light bodied impression material (Express XT, 3M ESPE, Seefeld, Germany) on the prepared teeth.



Fig. 3: Gingival Cord Placement

Ceramic laminate veneer restorations contain a lithium disilicate-reinforced glass ceramic material (IPS e.max Press, Ivoclar-Vivadent, Liechtenstein), using the heat press technique. A layering ceramic (IPS e.max Ceram, Ivoclar-Vivadent) strengthen the incisal edge optical characteristics was used the impressions were send to laboratory for further procedure. No temporation were done due to minimal preparation of the tooth surfaces. Each veneer was tried individually to assess the fit. Once the patient is happy and had approved the final aesthetics, the restorations were prepared for cementation. (Fig. 4).




Fig. 4: Completed veneers on working cast

The inner surface of veneers etched with 5% hydrofluoric acid (IVOCLAR VIVADENT) for or 60 seconds. The acid was thoroughly cleansed with air-water spray. It must be ensured that all the residues of acid remaining on the surface was cleaned properly.

Restorations were dried and silane primer was applied to the fitting surface, which helped to provide a chemical covalent bond to the ceramic.⁶

Teeth preparation were cleaned with polishing paste PROXYT IVOCLAR VIVADENT properly. (Fig. 5)



Fig. 5: Cleaned With Polishing Paste

37% phosphoric acid gel was applied to the preparation for 30 seconds and cleaned properly. Bonding Agent TETRIC N BOND was applied on the surface of Teeth preparation and scrubbed for 10 sec. Resin cement (light cure) Variolink N LC was applied on Veneer restoration and then restoration was seated on the tooth preparation with a gentle force.

All the excess cement around the margins were cleaned up properly. A #12 blade was used to carefully remove excess cement. Occlusion was carefully checked initially with centric occlusion followed by other excursive movements. (Fig. 6)



Fig. 6: Post Operative Photograph

Discussion

The hue, value and chroma of the remaining dental structure and the thickness of the ceramic veneers leads the treatment towards the different restorative strategies. They are indicated in the cases where abrasion, coronal fracture diastema tooth discoloration and slightly deranged occlusion. The better esthetic prognosis with preparations limited only in the enamel were the main reason for this treatment option.

Glass ceramic does have better bonding ability as compared to conventional restorative materials. The role of hydrofluoric acid in acid aching and silane coupling agent leads to increase the retention.⁷ The preparation which are wntirely in the enamel have excellent bonding as compared with the preparation which involves the dentinal structure.⁸

The tri-in paste which affects the better esthetics were used to select cement colour after the silane couplong agent was applied.¹⁰ It is washed out with water spray followed by air spray which helps in achievening the better bond strength of the tooth with the ceramics 6.11.while processing, some part of the unreacted silane coupling agents are remained unreacted .this unreacted part must be completely removed with water at room temperature. The presence of them can alter the coupling of the luting material to the ceramic by hydrolysis. This rinsing procedure can

not affect the inner part of the glass ceramic as it is hydrolytically stable due to the presence of covalent bonds with the silica.^{12,13}

The ideal cement for cementation is light cured resin based cement. It has the extra advantage of having longer working time and increased bond strength where working time is the one of the major and crucial part of the placement and the cementation of the veneers.^{14,15} The main aim of using light cured cement is that it can easily pass through the veneers as they contained reduced thickness and high translucency. The mechanical properties and cementation properties have better influence of light.¹⁶ Vehicle cementing with the dual cure resins, the light activation must be used as it has a critical role on the restorative materials degree of conversion.¹⁷

Another important matter is that not all the curing lights have equal intensities of light transmission through ceramics.¹⁸ It can only be possible with the use of fiber optic or polymer light guide tip.¹⁹ Due to this fact, the veneers must be light activated through incisal, medium and cervical part on both the sides.

The complete success is achieved through patient education and motivation toward the good oral health. The regular evaluation and patient contribution have major role in better prognosis of the treatment as well.

Conclusion

It can be concluded that the reproduction of the life like aesthetic appearance of natural teeth can be gained with the help of Porcelain Veneer. The long-term clinical success of porcelain veneers depends on a careful case selection and diagnostic approach, as well as accurate and appropriate tooth preparation and adhesive bonding procedures.

References

1. Guess PC, Schultheis S, Bonfante EA, Coelho PG, Ferencz JL, Silva NR. All-ceramic systems: laboratory and clinical performance. *Dental Clinics*. 2011 Apr 1;55(2):333-52.
2. Bloom DR, Padayachy JN. Aesthetic changes with four anterior units. *British dental journal*. 2006 Feb 11;200(3):135.
3. Radz GM. Minimum thickness anterior porcelain restorations. *Dental Clinics*. 2011 Apr 1;55(2):353-70.
4. Schmidt KK, Chiayabutr Y, Phillips KM, Kois JC. Influence of preparation design and existing condition of tooth structure on load to failure of ceramic laminate veneers. *Journal of Prosthetic Dentistry*. 2011 Jun 1;105(6):374-82.
5. Vargas MA, Bergeron C, Diaz-Arnold A. Cementing all-ceramic restorations: recommendations for success. *The Journal of the American Dental Association*. 2011 Apr 1;142:20S-4S.
6. Pegoraro TA, da Silva NR, Carvalho RM. Cements for use in esthetic dentistry. *Dental Clinics*. 2007 Apr 1;51(2):453-71.
7. Land MF, Hopp CD. Survival rates of all-ceramic systems differ by clinical indication and fabrication method. *Journal of Evidence Based Dental Practice*. 2010 Mar 1;10(1):37-8.
8. De Munck JD, Van Landuyt K, Peumans M, Poitevin A, Lambrechts P, Braem M, Van Meerbeek B. A critical review of the durability of adhesion to tooth tissue: methods and results. *Journal of dental research*. 2005 Feb;84(2):118-32.
9. Li Y. Safety controversies in tooth bleaching. *Dental Clinics*. 2011 Apr 1;55(2):255-63.
10. ALGhazali N, Laukner J, Burnside G, Jarad FD, Smith PW, Preston AJ. An investigation into the effect of try-in pastes, uncured and cured resin cements on the overall color of ceramic veneer restorations: an in vitro study. *Journal of dentistry*. 2010 Jan 1;38:e78-86.
11. Manso AP, Silva NR, Bonfante EA, Pegoraro TA, Dias RA, Carvalho RM. Cements and adhesives for all-ceramic restorations. *Dent Clin North Am*. 2011;55:311-32.
12. Manso AP, Silva NR, Bonfante EA, Pegoraro TA, Dias RA, Carvalho RM. Cements and adhesives for all-ceramic restorations. *Dental Clinics*. 2011 Apr 1;55(2):311-32.
13. Hooshmand T, van Noort R, Keshvad A. Storage effect of a pre-activated silane on the resin to ceramic bond. *Dental Materials*. 2004 Sep 1;20(7):635-42.
14. Da Cunha LF, Reis R, Santana L, Romanini JC, Carvalho RM, Furuse AY. Ceramic veneers with minimum preparation. *European journal of dentistry*. 2013 Oct;7(4):492.
15. Walls AW. The use of adhesively retained all-porcelain veneers during the management of fractured and worn anterior teeth: Part 2. Clinical results after 5 years of follow-up. *British dental journal*. 1995 May 6;178(9):337.
16. Pick B, Gonzaga CC, Junior WS, Kawano Y, Braga RR, Cardoso PE. Influence of curing light attenuation caused by aesthetic indirect restorative materials on resin cement polymerization. *European journal of dentistry*. 2010 Jul;4(3):314.
17. Di Francescantonio M, Aguiar TR, Arrais CA, Cavalcanti AN, Davanzo CU, Giannini M. Influence of viscosity and curing mode on degree of conversion of dual-cured resin cements. *European journal of dentistry*. 2013 Jan;7(1):81.
18. Ozturk B, Cobanoglu N, Cetin AR, Gunduz B. Conversion degrees of resin composites using different light sources. *European journal of dentistry*. 2013 Jan;7(1):102.
19. Galvão MR, Caldas SG, Bagnato VS, de Souza Rastelli AN, de Andrade MF. Evaluation of degree of conversion and hardness of dental composites photo-activated with different light guide tips. *European journal of dentistry*. 2013 Jan;7(1):86.